



Accura[®] e-Stone[™] Material

For use with solid-state stereolithography (SLA) Systems

Post-Cured Material

MEASUREMENT	CONDITION	METRIC	U.S.
Tensile Strength (MPa/PSI)	ASTM D 638	37-39	5400-5600
Tensile Modulus (MPa/KSI)	ASTM D 638	1500-1750	220-250
Elongation at Break (%)	ASTM D 638	10-23 %	10-23 %
Flexural Strength (MPa/PSI)	ASTM D 790	54-59	7800-8500
Flexural Modulus (MPa/KSI)	ASTM D 790	1350-1750	220-250
Impact Strength (J/m /Ft-lbs/in)	ASTM D 256	18-25	0.2-0.5
Heat Deflection Temperature	ASTM D 648 @ 66 PSI @ 264 PSI	58-63 °C 51-55 °C	145 °F 131 °F
Glass Transition (T _g)	DMA, E''	60 °C	140 °F
Hardness, Shore D		80	80

Liquid Material

MEASUREMENT	CONDITION	VALUE
Viscosity	@ 30 °C (86 °F)	220 cps
Penetration Depth (Dp)		4.2 mils
Critical Exposure (Ec)		10.5 mJ/cm ²
Color		Peach
Solid Density	@ 25 °C (77 °F)	1.19 g/cm ³ at 25 °C
Liquid Density	@ 25 °C (77 °F)	1.13 g/cm ³ at 25 °C
Tested Build Styles		EXACT [™]

Features

- Durable
- Accurate
- Selection of color
- Digital production

Benefits

- Compatible with standard dental lab practices
- Reduce breakage vs. plaster
- Decreased steps vs. impression based systems
- Increased visual detail for better margin viewing
- Reproducible and archivable for easy remakes

Applications

- Replacement for dental stone
- Crown and bridge restorations
- Orthodontic working and study models



www.3dsystems.com

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2020 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. 3D Systems, the 3D Systems logo, and Accura are registered trademarks of 3D Systems, Inc.